

測試介質 - 水

材質	WCB/A105		LCC/LF2		WC6/F11		WC9/F22		C5/F5		CF8/F304		CF8M/F316	
Class	shell	closure	shell	closure	shell	closure	shell	closure	shell	closure	shell	closure	shell	closure
150#	450	315	450	320	450	320	450	320	450	320	425	305	425	305
300#	1125	812	1125	825	1125	825	1125	825	1125	825	1100	795	1100	795
600#	2225	1630	2250	1650	2250	1650	2250	1650	2250	1650	2175	1585	2175	1585
800#	2965	2175	3000	2200	3000	2200	3000	2200	3000	2200	2900	2115	2900	2115
900#	3350	2445	3375	2475	3375	2475	3375	2475	3375	2475	3250	2380	3250	2380
1500#	5575	4080	5625	4125	5625	4125	5625	4125	5625	4125	5400	3960	5400	3960
2500#	9275	6790	9375	6875	9375	6875	9375	6875	9375	6875	-----	-----	-----	-----

公制單位：kg/cm²

材質	WCB/A105		LCC/LF2		WC6/F11		WC9/F22		C5/F5		CF8/F304		CF8M/F316	
Class	shell	closure	shell	closure	shell	closure	shell	closure	shell	closure	shell	closure	shell	closure
150#	32	23	32	23	32	23	32	23	32	23	30	22	30	22
300#	80	58	80	58	80	58	80	58	80	58	78	56	78	56
600#	157	115	158	116	158	116	158	116	158	116	153	112	153	112
800#	209	153	211	155	211	155	211	155	211	155	203	149	203	149
900#	236	172	237	174	237	174	237	174	237	174	229	168	229	168
1500#	392	287	396	290	396	290	396	290	396	290	380	279	380	279
2500#	653	478	659	484	659	484	659	484	659	484	-----	-----	-----	-----

1. 壓封閉測試為 80 Psi (6 kg/cm²)
2. 依據 **ANSI B16.34-1988** (測試溫度：-20~100°C)
3. 800# 依據 **API 602-1993** (測試溫度：-20~100°C)

志明

手機:0927872155 歡迎電洽

24H 網路 FAX:07-7247299

E mail:ming690708@gmail.com

<http://goo.gl/N14M>